## Product Information

## AVENO MBike 20W-50

0002-000712



## Description

AVENO MBike 20W-50 is a motor oil based on hydrocrack oils with selected additives for demanding 4-stroke motorcycles. It is characterized by a very high oxidation stability, excellent lubricating film adhesion and reliability under any load and is specially designed for wet and oil-lubricated clutches. AVENO MBike 20W-50 protects the engine from deposits and ensures a long service life.

## Instructions for use

It is the ideal for 4-stroke engines. The formulation guarantees maximum protection for all engine components. It makes shifting gears easier and offers much smoother handling. The efficiency is reflected in the verylow friction of engine components while maintaining maximum performance. It is ideally suited for road use.

Quality classification				
Specification				
• API SN		• JASO MA2		
Properties				
Reduction of wear and tear		Perfectly matched to road	Perfectly matched to road use	
Very stable viscosity index		<ul> <li>Prevention of silting, varnishing, coking and corrosion</li> </ul>		
Rapid oiling of the engine		<ul> <li>Prevention of oil-related deposits in combustion chambers, in the piston ring zone and</li> <li>on the valves</li> </ul>		
Technical specifications				
Properties	Data	Unit	Testing under	
Kinematic Viscosity at 40°C	161.5	mm²/s	DIN 51659-2:2017-02	
Kinematic Viscosity at 100°C	17.9	mm²/s	DIN 51659-2:2017-02	
Viscosity Index	123		DIN ISO 2909:2004-08	
Appearance	YELLOWBROWN		VISUELL	
Density at 15°C	874	kg/m³	DIN EN ISO 12185:1997-11	
Flash Point (COC)	266	°C	DIN EN ISO 2592:2018-01	
Total Base Number (TBN)	7.5	mgKOH/g	ASTM D 2896:2021	

Deutsche Ölwerke Lubmin GmbH | Freesendorfer Weg 4 | 17509 Lubmin | Phone +49 38354 / 179530 | Fax +49 38354 / 179579

Notice: To the best of our knowledge, all of the information provided was in accordance with the latest findings and developments of the Deutsche Ölwerke Lubmin GmbH. Our products are subject to continuous development. For this reason, our products, the manufacturing processes and all related information on this product page are subject to change at any time and without notice, unless customer-specific agreements exist. The data listed are based on standardized test procedures under appropriate laboratory conditions and are to be regarded as general, non-binding reference values.