Product Information

AVENO MBike 10W-50

0002-000809



Description

AVENO MBike 10W-50 is a motor oil based on hydrocrack oils with selected additives for demanding 4-stroke motorcycles. It is characterized by a very high oxidation stability, excellent lubricating film adhesion and reliability under any load and is specially designed fordesigned for wet and oil-lubricated clutches. AVENO MBike 10W-50 protects the engine from deposits and ensures a long service life.

Instructions for use

AVENO MBike 10W-50 is suitable as motor oil for all air- and water-cooled 4-stroke motorcycles if a viscosity of 10W-50 is required. The operating instructions of the engine manufacturer must be observed!

Quality classification				
Specification				
• API SN		• JASO MA2	• JASO MA2	
Properties				
• Very good shear stability		 High safety reserves even under 	 High safety reserves even under boundary lubrication conditions 	
 Very good cold start properties 		 Optimum function of engine, clu 	 Optimum function of engine, clutch and transmission 	
Prevention of premature wear		 Very good resistance to oxidation 	 Very good resistance to oxidation and high temperature engine deposits 	
 Tried and tested additives 				
Technical specifications				
Properties	Data	Unit	Testing under	
Kinomatic Viscosity at 40°C	122.0	mm ² /c	DIN 51650 2:2017 02	

Properties	Data	Unit	Testing under
Kinematic Viscosity at 40°C	123.0	mm²/s	DIN 51659-2:2017-02
Kinematic Viscosity at 100°C	17.8	mm²/s	DIN 51659-2:2017-02
Viscosity Index	160		DIN ISO 2909:2004-08
Appearance	YELLOWBROWN		VISUELL
Viscosity CCS at -25°C	6700	mPa*s	ASTM D 5293:2020
Density at 15°C	860	kg/m³	DIN EN ISO 12185:1997-11
Pour Point	-39	°C	ASTM D 7346:2015
Total Base Number (TBN)	7.6	mgKOH/g	ASTM D 2896:2021

Notice: To the best of our knowledge, all of the information provided was in accordance with the latest findings and developments of the Deutsche Ölwerke Lubmin GmbH. Our products are subject to continuous development. For this reason, our products, the manufacturing processes and all related information on this product page are subject to change at any time and without notice, unless customer-specific agreements exist. The data listed are based on standardized test procedures under appropriate laboratory conditions and are to be regarded as general, non-binding reference values.